



ANTIRUST

DESCRIPTION: Alkyd resin based , protection Primer for metal surfaces.

CHARACTERISTIC :

- Easily appliable
- High covering and aghesiveness ability .
- Easily dispersal , salty , resistant against alkali and outside effects.
- Anticorrosive

APPLICATION SURFACES:

Can be applied on all kinds of metal surfaces.

TECHNICAL INFORMATION:

Structure : Anticorrosive Consumption : 12-14 (m²/lt)

Thinning Ratio : In brush , roller and spraying applications % 5 -10 with thinner. Application tools: Brush , roller , spray gun.

Drying : Dust repulsive; after 15 - 20 minutes;Hard dry for topcoat application:after 8 - 10 hours Viscosity : 110 KU ± 10 (23 ° C)

Density : 1,43 ± 0,05 (g / cm³) Amount of solid : (75 ± 2)% Thickness of dry coat: 40 ± 5 micron
Thickness of wet coat: 80 ± 5 micron

SURFACE PREPARATION:

- Surface should be free from all grease , dirt ,rust , remainings and foreign materials. Surface should be obtained as dry.
- Welded and sharp places should be smooted.

CAUTION:

- Avoid getting eye and skin contact. In case wash with plenty of water.
- Preserve in a tightly closed cape.
- Keep above the reach of children
- Do not dump into sewer system.

STORAGE: STORAGE

Keep at a cool and clean place away from sun light. It can be stored unopened 1 year at room temperature.

PACKAGING:

18kg-4 kg-1 kg